

## Specifications for Asahi Sn60Pb40 (CF-10A) Core Wire

<b>1) Alloy Composition:</b>	<b>Sn60Pb40</b>	
<b>Standard</b>	<b>JIS Z 3282: 2006 (Wt%)</b>	
Sn	60 +/- 0.5	
Pb	Remainder	
Sb	0.20 max	
Bi	0.10 max	
Cd	0.002 max	
Cu	0.08 max	
Au	0.05 max	
In	0.10 max	
Ag	0.10 max	
Al	0.001 max	
As	0.03 max	
Fe	0.02 max	
Ni	0.01 max	
Zn	0.001 max	
<b>2) Physical Characteristics:</b>		
Specific Gravity	8.53	
Liquidus Temperature	191 °C	
Solidus Temperature	183 °C	
<b>3) Core Flux Characteristics:</b>		
Flux Activity Classification	<b>Specifications</b>	<b>Standards / Test Methods</b>
Flux Content (wt%)	ROH1	IPC J-STD-004A
Halide Content	2.0 +/- 0.3	Singapore Asahi
Copper Mirror Test	0.45 wt%	IPC-TM-650 2.3.35B
Spread Factor	Classified as "H",	JIS Z 3197: 1999 8.1.4.2.2
Surface Insulation Resistance	Pass	IPC-TM-650 2.3.32
(85°C / 85 %RH)	>90% (Sn60Pb40)	JIS Z 3197: 1999 8.4.2
Water Extract Resistivity	>1 x 10 <sup>8</sup> Ω	JIS Z 3197: 1999 8.3.1.1
	>1 x 10 <sup>11</sup> Ω	IPC-TM-650 2.6.3.3
	>1 x 10 <sup>4</sup> Ω-cm	JIS Z 3197: 1999 8.5.4
		JIS Z 3197: 1999 8.1.1
<b>4) Standard Packing:</b>		
( ) 0.25 kg per roll.	100 rolls per carton	
( ) 0.5 kg per roll.	50 rolls per carton.	
( ) 1 kg per roll.	20 rolls per carton.	

---

### SINGAPORE ASAHI CHEMICAL & SOLDER INDUSTRIES PTE LTD

47 Pandan Road S(609288)  
Tel:6262-1616 Fax:6261-6311  
Website: <http://www.asahisolder.com> E-mail: [sales@sinasahi.com.sg](mailto:sales@sinasahi.com.sg)

---